



Deckdrain 2540S/NW20XUV

Deckdrain 2540S/NW20XUV is a geocomposite drainage layer comprising a medium weight geotextile filter, thermally bonded on one side of a high strength single cusped HDPE (High Density Polyethylene) core. The textile filter has a flap extending beyond the core on one edge. The product is practically impermeable one side. Its main application is as a drainage layer to the external walls, floor and roof of underground structures.

Geocomposite Properties		
Thickness at 2kPa	(mm) 26.9	±10% EN ISO 9863-1
Mass per unit area	(g/m ²) 2500	approx EN ISO 9864
Tensile Strength MD/CMD	(kN/m) 34/34	-10% EN ISO 10319
Elongation at peak MD/CMD	(%) 50/50	nominal EN ISO 10319
CBR Puncture Resistance	(N) 5600	-20% EN ISO 12236
Perpendicular Water Inflow	(dimple side only)	
Water flow at 50mm head	(l/m ² .s) 72	±30% EN ISO 11058
At 2kPa permeability (<i>coefficient</i>)	(m/s) 2.8 x 10 ⁻³	±30% EN ISO 11058
Breakthrough head	(mm) 0	nominal

In-plane Water Flow MD and CMD	HG =1.0		HG=0.1		Hydraulic gradient
at 20kPa Confining Pressure	(l/m.s) 11.75	-20%	4.05	-20%	EN ISO 12958
at 100kPa Confining Pressure	(l/m.s) 9.15	-20%	2.85	-20%	EN ISO 12958
at 200kPa Confining Pressure	(l/m.s) 7.95	-20%	2.35	-20%	EN ISO 12958

with soft foam contact surfaces to simulate textile intrusion into the core due to soil pressure.

with soft foam contact surfaces to simulate textile intrusion into the core due to soil pressure

Green-tech endeavour to ensure that the information given on this technical data sheet is accurate, but accept no liability for its use or its suitability for particular application.

Rabbit Hill Business Park, Great North Road, Arkendale, Knaresborough HG5 0FF

T: 01423 332100 E: sales@green-tech.co.uk W: www.green-tech.co.uk Facebook: @greentechuk Twitter: @greentechltd





Geocomposite Properties Continued		
Resistance to weathering	The geotextile has high UV stabilisation which may allow exposure up to 12 months depending on location	EN 12224
Resistance to chemicals	Excellent	EN 14030
Design life	120 years (manufacturer's declaration)	

Geotextile Properties		
Thickness at 2kPa	(mm) 1.75	±20% EN ISO 9863-1
Tensile Strength MD/CMD	(kN/m) 20 / 20	-13% EN ISO 10319
Pore size O_{90}	(μ m) 70	±30% EN ISO 12956
CBR Puncture Resistance	(N) 3400	-20% EN ISO 12236
Dynamic Perforation Cone Drop	(mm) 17	+20% EN ISO 13433
Type and Material	Non-woven needle-punched and heat-treated long staple fibre polypropylene.	

Product Dimensions	
Standard Roll Dimensions	0.915m x 40m. Other sizes on request.

Notes

1. The values given are indicative and correspond to nominal results obtained in our laboratories and testing institutes. In line with our policy of continuous improvement the right is reserved to make changes without notice at any time.
2. The tolerance on roll length is 1.5% and on roll width is 1.0%.
3. Guidance on interface shear strength, creep and certain other parameters is available. Site specific tests are strongly recommended.
4. Final determination of the suitability of any information is the sole responsibility of the user. Green-tech will be pleased to discuss the use of this or any other product but responsibility for selection of a material and its application in any specific project remains with the user.



Green-tech endeavour to ensure that the information given on this technical data sheet is accurate, but accept no liability for its use or its suitability for particular application.

Rabbit Hill Business Park, Great North Road, Arkendale, Knaresborough HG5 0FF

T: 01423 332100 E: sales@green-tech.co.uk W: www.green-tech.co.uk Facebook: @greentechuk Twitter: @greentechltd

