## gtDECKDRAIN 600S/NW8

Soils, Growing Media & Barks

green-tech

A lightweight, high performance drainage layer with integrated filter geotextile to eliminate clogging for intensive green roofs. gtDeckdrain has been developed to provide high flow capacity and waterproofing. It is durable and sufficiently robust to resist mechanical stresses imposed during installation and throughout its lifespan.

GEOCOMPOSITE PROPER	RTIES					
Thickness at 2kPa	(mm)	6.1			±10%	EN ISO 9863-1
Mass per unit area	(g/m²)	670			approx	EN ISO 9864
Tensile strength MD / CMD	(kN/m)	9.5 / 9.5			-13%	EN ISO 10319
Elongation at peak MD / CMD	(%)	40 / 50			nominal	EN ISO 10319
CBR puncture resistance	(N)	2 250			-20%	EN ISO 12236
Perpendicular Water Inflow	(dimple side only)					
Water flow at 50mm head	(l/m²·s)	103			±30%	EN ISO 11058
At 2kPa permeability (coefficient)	(m/s)	2.6 x 10 <sup>-3</sup>			±30%	EN ISO 11058
Breakthrough head	(mm)	0			nominal	
In-plane water flow MD <sup>3</sup>		<u>HG = 1.0</u>		<u>HG = 0.1</u>		<u>Hydraulic gradient</u>
at 20kPa confining pressure	(l/m·s)	1.45	±0.25	0.45	±0.09	EN ISO 12958
at 100kPa confining pressure	(l/m·s)	1.25	±0.23	0.38	±0.10	EN ISO 12958
at 200kPa confining pressure	(l/m·s)	1.05	±0.21	0.29	±0.07	EN ISO 12958
with <b>soft foam</b> contact surfaces to flow rates shown above are all equ						res of the
Resistance to weathering		To be covere	d in 28 days			EN 12224
Resistance to chemicals		Excellent				EN 14030
Design life	120 years (manufacturer's declaration)					
<b>GEOTEXTILE PROPERTIES</b>	S					
Thickness at 2kPa	(mm)	1.2			±20%	EN ISO 9863-1
Tensile strength MD/CMD	(kN/m)	9.5 / 9.5			-13%	EN ISO 10319
Pore size 0 <sub>90</sub>	(µm)	120			±30%	EN ISO 12956
CBR puncture resistance	(N)	1 600			-20%	EN ISO 12236
Dynamic perforation cone drop	(mm)	32			+20%	EN ISO 13433
Type and material	Non-woven needle-punched and heat-treated long staple fibre polypropylene					
PRODUCT DIMENSIONS						
Standard roll dimensions	1.1 m x 50 m	or 2.2 m x 25 m	n. Other sizes	on request.		

NOTES

 The values given are indicative and correspond to nominal results obtained in laboratories and testing institutes. In line with policies of continuous improvement the right is reserved to make changes without notice at any time.

2. Final determination of the suitability of any information is the sole responsibility of the user.

3. CMD flow is typically 80% of the value in the MD.

4. The tolerance on roll length is  $\pm 1.5\%$  and on roll width is  $\pm 1.0\%$  in multi-core products this may manifest itself between core elements.

5. Guidance on interface shear strength, creep and certain other parameters is available. Site specific tests are strongly recommended.

Green-tech endeavour to ensure that the information given on this technical data sheet is accurate but accept no liability for its use or suitability for particular application.

01423 332100 sales@green-tech.co.uk www.green-tech.co.uk

