gtDECKDRAIN 700S/NW8

green-tech Pbnt - Protect - Enhance - Improve

Soils, Growing Media & Barks

A lightweight, high performance drainage layer with integrated filter geotextile to eliminate clogging for intensive green roofs. gtDeckdrain has been developed to provide high flow capacity and waterproofing. It is durable and sufficiently robust to resist mechanical stresses imposed during installation and throughout its lifespan.

GEOCOMPOSITE PROPER	RTIES					
Thickness at 2kPa	(mm)	7.6			±10%	EN ISO 9863-1
Mass per unit area	(g/m²)	870			approx	EN ISO 9864
Tensile strength MD / CMD	(kN/m)	9.5 / 9.5			-13%	EN ISO 10319
Elongation at peak MD / CMD	(%)	40 / 50			nominal	EN ISO 10319
CBR puncture resistance	(N)	2 400			-20%	EN ISO 12236
Perpendicular Water Inflow	(dimple side only)					
Water flow at 50mm head	(l/m²⋅s)	100			±30%	EN ISO 11058
At 2kPa permeability (coefficient)	(m/s)	2.6 x 10 ⁻³			±30%	EN ISO 11058
Breakthrough head	(mm)	0			nominal	
In-plane water flow MD ³		<u>HG = 1.0</u>		<u>HG = 0.1</u>		<u>Hydraulic gradient</u>
at 20kPa confining pressure	(l/m·s)	2.40	±0.40	0.67	±0.13	EN ISO 12958
at 100kPa confining pressure	(l/m·s)	1.95	±0.33	0.53	±0.11	EN ISO 12958
at 200kPa confining pressure	(l/m·s)	1.45	±0.24	0.37	±0.07	EN ISO 12958
with soft foam contact surfaces to flow rates shown above are all equ						ssures of the
Resistance to weathering	To be covered in 28 days				EN 12224	
Resistance to chemicals	Excellent				EN 14030	
Design life	120 years (manufacturer's declaration)					
GEOTEXTILE PROPERTIES	S					
Thickness at 2kPa	(mm)	1.2			±20%	EN ISO 9863-1
	(mm) (kN/m)	1.2 9.5 / 9.5			±20% -13%	EN ISO 9863-1 EN ISO 10319
Thickness at 2kPa						
Thickness at 2kPa Tensile strength MD/CMD	(kN/m)	9.5 / 9.5			-13%	EN ISO 10319
Thickness at 2kPa Tensile strength MD/CMD Pore size 0 ₉₀	(kN/m) (μm)	9.5 / 9.5 120			-13% ±30%	EN ISO 10319 EN ISO 12956
Thickness at 2kPa Tensile strength MD/CMD Pore size 0 ₉₀ CBR puncture resistance	(kN/m) (μm) (N) (mm)	9.5 / 9.5 120 1 600 32	ed and heat-tr	eated long stap	-13% ±30% -20%	EN ISO 10319 EN ISO 12956 EN ISO 12236 EN ISO 13433
Thickness at 2kPaTensile strength MD/CMDPore size 0 ₉₀ CBR puncture resistanceDynamic perforation cone drop	(kN/m) (μm) (N) (mm)	9.5 / 9.5 120 1 600 32	ed and heat-tr	eated long stap	-13% ±30% -20% +20%	EN ISO 10319 EN ISO 12956 EN ISO 12236 EN ISO 13433

NOTES

es given are indicative and correspond to nominal results obtained in laboratories and

1. The values given are indicative and correspond to nominal results obtained in laboratories and testing institutes. In line with policies of continuous improvement the right is reserved to make changes without notice at any time.

2. Final determination of the suitability of any information is the sole responsibility of the user.

3. The tolerance on roll length is $\pm 1.5\%$ and on roll width is $\pm 1.0\%$ in multi-core products this may manifest itself between core elements.

4. Guidance on interface shear strength, creep and certain other parameters is available. Site specific tests are strongly recommended.

Green-tech endeavour to ensure that the information given on this technical data sheet is accurate but accept no liability for its use or suitability for particular application.

01423 332100 sales@green-tech.co.uk www.green-tech.co.uk

